

LINETESTLAB

Zebco


Cajun

Monofilament

10lb

Tensile Test Results

Capacity	Force (lb)	Stretch%
10%	1lb	3.5
20%	2lb	11.7
30%	3lb	21.5
40%	4lb	29.5
50%	5lb	34.8
60%	6lb	39.7
70%	7lb	43.7
80%	8lb	47.3
90%	9lb	50.8
100%	10lb	54.3
MAX	13.23	81.5
Average of 6 Tests		



Palomar Knot Test Results

Average Break Force (lb)

13.2

Average of 5 Tests

Line Thickness

Average Thickness (in)

0.01179

Average of 5 Tests

Abrasion Test Results

Average Time To Break (sec)

84.4

Average of 1 Tests

Test Notes:

Awesome palomar knot test results.
 With only 3.5% stretch at 10% I suspect this will be very sensitive.
 For cheap line I'm very impressed with these results.
 Abrasion test is preliminary: Waiting on standardized abrasive.

Test Images

Normal Photo



Knot Break Photo



Tensile Test Break Photo



Abrasion Break Photo



Product Photo

